



Technical Data Sheet

Epilight™ 5845 visible blue dye

DESCRIPTION

Suitable for thermoplastic processing

Very good light fastness

Excellent thermal stability

PROPERTIES

Absorption maximum, λ max: 631 nm in chloroform

Absorptivity in chloroform: $39.5 \text{ L g}^{-1} \text{ cm}^{-1}$

Appearance: blue powder


Melting point: 166°C

Solubility in grams/100 grams of solvent:

Xylene 15 grams

Acetone 2.0 grams

Methylene chloride 25 grams



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.