

Technical Data Sheet

Epilight™9849 IR absorbing dye

DESCRIPTION

Suitable for thermoplastic processing

Produces light green filter


PROPERTIES

Absorption maximum, λ max: 905 nm (chloroform); 911 nm (polycarbonate)

Absorptivity in chloroform: $90 \text{ L g}^{-1} \text{ cm}^{-1}$

Appearance: dark green powder

absorbance spectrum of Epilight 9849 in chloroform



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.