

## **Technical Data Sheet**

## **Epolight™ 4113 Near Infrared Dye**

## **DESCRIPTION**

Contains platinum

Suitable for plastic applications

Excellent visible light transmission

**Excellent light stability** 

Excellent thermal stability

## **PROPERTIES**


Absorption maximum,  $\lambda$  max: 833 nm Absorptivity in chloroform: 65 L g<sup>-1</sup> cm<sup>-1</sup>

Appearance: dark brown powder

Melting point: 270 - 274°C

Solubility in grams/100 grams of solvent:

Chloroform 0.49 grams MEK 0.38 grams Xylene 0.12 grams



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information from this data sheet or the products to which the information refers.

© Epolin All Rights Reserved rev 04/13